



Sterling Polyester

Polyester Powder Coating ini diformulasikan secara khusus untuk aplikasi outdoor, dimana ketahanan terhadap sinar UV dan ketahanan terhadap perubahan cuaca sangat diperlukan. Polyester powder coating dapat diaplikasikan pada permukaan metal dan alluminium. Sterling Polyester Powder Coating merupakan cat khusus industri.



*Warna dan gloss terbatas.



*Polyester kami sudah TGIC - FREE!





STERLING®

POWDER COATINGS

Sterling Polyester Specifications

Gloss	70 ± (60° geometry)	
Specific Gravity	1.68 ± 0.05	
Recommended Bake	180°C - 200°C @10 minutes (metal Temp.)	
Film Thickness	60 - 80 micron	
Impact Resistance	100 inch pounds direct	ASTM D-2794
Hardness	H-2H pencil	ASTM D-3363
Flexibility	1/8 inch mandrel	ASTM B-522
Adhesion	100% crosshatch	ASTM D-3359
Overbake Resistance	100% time at temperature	
Corrosion	1000 hrs ≤ 1.0 mm creep	ASTM B-117
Humidity	1000 hrs no blisters	ASTM D-2247
Weatherability	recommended for outdoor applications	
Storage	9 months when stored at 25°C	



Diproduksi oleh:



PT. SAN CENTRAL INDAH
Bandung - Indonesia