



Sterling Epoxy Polyester

Epoxy Polyester Powder Coating diformulasikan secara khusus untuk aplikasi indoor, dimana kebutuhan warna serta tingkat gloss dapat disesuaikan dengan kebutuhan. Epoxy Polyester Powder Coating ini sangat cocok untuk: Dish Washing, Electrical Panel, Office Furniture, Kompor Gas, dll. dimana kebutuhan 'mechanical property dan scratch resistant' sangat diperlukan. Epoxy Polyester Powder Coating ini sangat baik di 'flexibility dan flow'.



***Mohon diperhatikan bahwa Epoxy Polyester Powder Coating ini tidak cocok digunakan untuk aplikasi outdoor!**





STERLING®

POWDER COATINGS

Sterling Epoxy Polyester Specifications

Gloss	40 ± 5.0 %(60° geometry)	
Specific Gravity	1.48 ± 0.05	
Recommended Bake	180°C - 200°C @10 minutes (metal Temp.)	
Film Thickness	60 - 80 micron	
Impact Resistance	160 inch pounds direct	ASTM D-2794
Hardness	H-2H pencil	ASTM D-3363
Flexibility	1/4 inch mandrel	ASTM B-522
Adhesion	100% crosshatch	ASTM D-3359
Overbake Resistance	100% time at temperature	
Corrosion	1000 hrs ≤ 1.0 mm creep	ASTM B-117
Humidity	1000 hrs no blisters	ASTM D-2247
Weatherability	Not recommended for outdoor applications	
Storage	9 months when stored at 25°C	



Diproduksi oleh:



PT. SAN CENTRAL INDAH
Bandung - Indonesia